

VOLUME-III: SECTION – I

TECHNICAL SPECIFICATIONS

Contents

3 Tubular Steel Poles for Overhead Lines
50

DDUGJY & IPDS/SBD/NIMM/R0

Tubular Steel Poles for Overhead Lines

SCOPE:

This specification covers the general requirements towards design, manufacture, testing at manufacturers works, supply and delivery for tubular steel poles of circular cross section (swaged type) for overhead lines.

STANDARD:

The tubular steel poles shall conform to the latest edition of Indian Standard specification IS: 2713 (Part – II, III): 1980 or any other authoritative standards (as amended up-to- date) except where specified otherwise in this specification.

Topography and Climatic Condition:

The materials offered, shall be suitable for operation in tropical climate and will be subjected to the sun and inclement weather and shall be able to withstand wide range of temperature variation. For the purpose of design, average atmospheric temperature may be considered to be 50°C with humidity nearing saturation.

Materials:

The materials used in construction of tubular steel poles shall be of the tested quality of steels of minimum tensile strength 410 MPa (: 42 Kgf/mm²).

The materials, when analysed in accordance with IS: 228 (Part-III: 1972) and IS : 228 (Part-IX) shall not show sulphur and phosphorous contents of more than 0.060 percent each.

Types, Size and construction:

Tubular Steel Poles shall be swaged type.

Swaged poles shall be made of seamless or welded tubes of suitable lengths swaged and jointed together. No circumferential joints shall be permitted in the individual tube lengths of the poles. If welded tubes are used they shall have one longitudinal weld seam only: and the longitudinal welds shall be staggered at each swaged joint.

Swaging may be done by any mechanical process. The upper edge of each joint shall be chamfered if at an angle of about 45°. The upper edge need not be chamfered if a circumferential weld is to be deposited in accordance with IS: 2713 (Part-II):1980.

The length of joints on swaged poles shall be in accordance with IS: 2713 (Par-II): 1980.

Poles shall be well-finished, clean and free from harmful surface defects. Ends of the poles shall be cut square. Poles shall be straight, smooth and cylindrical. The weld joints, if any, shall be of good quality, free from scale, surface defects, cracks, etc.

Tolerances for outside diameter, thickness, length, weight and straightness shall be in accordance with IS: 2713 (Part-II) : 1980.

The poles shall be coated with black bituminous paint conforming to IS: 158-1968 throughout, internally and externally, upto the level which goes inside the earth. The remaining portion of the exterior shall be painted with one coat of red oxide primer as specified in IS: 2074-979.

Earthing Arrangements:

For earthing arrangement a through hole of 14mm diameter shall be provided in each pole at a height of 300mm above the planting depth.

Tests and Test Certificates:

The following tests shall be conducted on finished poles :

Tensile test and chemical analysis for sulphur and phosphorous,
Deflection test,
Permanent set test, and
Drop test.

In addition to above verification of dimensions as per IS: 2713 (Part-III) : 1980 shall be carried out during acceptance lots.

Number of poles selected for conducting different tests shall be in accordance to IS: 2713 (Part-I) 1980.

Tests shall be carried out before supply of each consignment at the manufacturers works and test certificates should be submitted to the purchaser for approval prior to delivery.

Re-tests, if any, shall be made in accordance with IS: 2713 (Part-I) 1980.

Purchaser reserves the right to inspect during manufacturing and depute his representative to inspect/test at the works.

If any extra cost is required for carrying out the above specified tests, the same shall be borne by the manufacturer.

Marking:

The poles shall be marked with designation, manufacturer's identification, year of manufacture and name of the purchaser: Employer Name; Name of Scheme i.e. IPDS/DDUGJY/DP

The poles may also be marked with the ISI certification mark.

Guaranteed technical particulars:

The manufacturer shall furnish all necessary guaranteed technical particulars in the prescribed Performa enclosed hereinafter.

Performance:-

The manufacturer shall furnish a list of the major supplies effected during the last 3 (three) years indicating the volume of supply and actual delivery dates.

Manufacturer may not be considered if the past manufacturing experience is found to be less than 3 (three) years.

Deviation:-

Any deviation in technical specification shall be clearly indicated with sufficient reasons thereof. Purchaser shall however reserve the right to accept and/or reject the same without assigning any reasons what-so-ever.

ANNEXURE – „A“
**SPECIFIC TECHNICAL REQUIREMENTS FOR
TUBULAR STEEL POLES : SWAGED TYPE**

IS: 2713 (Pat-II and III): 1980 as amended upto date Swaged Type

	9-meters-long	8 meters long
1) Standard		
2) Type of Pole		
3) Designation	410 SP 31	410 SP 14
4) Overall Length	9 meters	8 meters
5) Planting depth	1.5 meters	1.5 meters
6) Height above ground	7.5 meters	6.50 meters
7) Effective length of Each section.		
a) Bottom	5.0 meters	4.50 meters
b) Middle	2.0 meters	1.75 meters
c) Top	2.0 meters	1.75 meters
8) Outside diameter and Thickness of each Section.		
a) Bottom	165.1x4.50 mm	139.7x4.85 mm
b) Middle	139.7x4.50 mm	114.3x4.50 mm
c) Top	114.3x3.65 mm	88.9x3.25 mm
9) Joint Length (in cm.):		
a) Bottom (J2)	30 cm.	30 cm.
b) Top (J1)	23 cm.	23 cm.
10) Approximate weight of Pole	147 Kg.	111 Kg.
11) Point of application of load below/top (mtr.)	0.3 mtr.	0.3 mtr.
12) Breaking load (inKgf)	517	453
13) Working load with factor of Safety : 2.5 (in Kgf)	207	181
14) Crippling load (inKgf)	367	322
15) Load for permanent set Not exceeding 13mm (in Kgf)	251	220
16) Load for Temporary Deflection of 157.5 mm (in Kgf)	139	131
17) Tolerance	As per IS : 2713 (Part-I & Part-III): 1980	
18) Finish	-do-	
19) Manufacturing clause	-do-	